

BLACKOUT TECHNICAL INFO

Flame Resistance: Bantex® 10 oz. Blackout resists combustion and will self-extinguish when the source of flame is removed.

Care Instructions: **Soils or Stains:** should be removed periodically for a fresh new appearance. Use neutral soap suds and lukewarm water, then rinse with water and allow to dry.

Hard to Clean Spots: Standard household/vinyl cleansers and/or soft bristle brush can be used for removing troublesome spots or stains. Heavy “dried on” soil may first require soaking to loosen. **DO NOT USE HARSH CLEANERS OR SOLVENTS.**

Laundering: Laundering is not recommended as this may substantially decrease the useful life of the fabric. If laundering is required, follow the procedures of the International Fabricare Institute.

1. Wash and rinse according to the “Synthetic Washing Procedure for Coated Fabrics” with temperatures not exceeding 100° F. (See chart below)

Operation	Water Level	Time	Maximum Temperature	Supplies
1st Suds	High	5 Min.	100° F	Neutral Soap & Alkali
2nd Suds	High	10 Min.	100° F	Neutral Soap & Alkali
1st Rinse	High	3 Min.	100° F	Water
2nd Rinse	Low	3 Min.	90° F	Sour to pH 5.0

2. Extract water with centrifugal extractor.
3. Tumble dry in a steam dryer (not gas) at 120° F maximum. For tailored, precise fitted items, tumble dry without heat or air dry. **DO NOT IRON.**

Specifications: Solid color - Black
74” wide
10 oz. per lineal yard
14% polyester and 86% flexible polyvinyl chloride
Excellent abrasion resistance, dimensional stability, and flexibility.
Chemical and mildew resistant.